

Product Description

A high performance chalk sealer and bonding coat for use on a variety of interior and exterior surfaces to include new and previously coated masonry and stucco; as well as previously painted wood, metal surfaces, PVC pipe and even glass to ensure proper adhesion of the topcoat.

Recommended Substrates <ul style="list-style-type: none"> Concrete, concrete block and stucco Poured and precast concrete Synthetic EIFS & synthetic stucco Cementitious & fiber cement siding Previously painted metals Wood and plywood 	Available bases 3690: Clear Available bases 3692: White	Product Data Product Type: Acrylic Emulsion
	Application: Brush, roller, airless or conventional spray Dry time @ 50% RH*: 30 min to touch 1-2 HRS recoat *dry times listed may vary according to the relative humidity, temperature, film build, color and air movement of the application environment Flash Point: >200°F Clean Up: Soap and water	Gloss @60°: 3690 1 - 10 3692 1 - 10 Wt Solids ±2%: 25% 33% Vol Solids ±2%: 20% 24% Wet Film Mils: 4.9 - 5.8 4-1 - 5.0 Dry Film Mils: 1.0 - 1.2 1.0 - 1.2 Coverage / Gal*: 275 - 325 320 - 390 * coverage and wet and dry millage will vary by substrate type and porosity. VOC gms p/L*: <200 <200 *less exempt solvents and before the addition of colorant Viscosity KU ±5: 70 80
Product Features <ul style="list-style-type: none"> Fast dry Locks down chalky surfaces Tenacious adhesion Promotes adhesion of the topcoat Soap and water clean up 	Compliance These products are VOC compliant based on limits provided by EPA, MPI GSP-1, LEEDv4 and OTC.	
Product Limitations This product is for use on properly prepared above grade vertical substrates.		

Surface Preparation

Caution! There is the potential to release lead dust if you sand scrape or remove old paint. Lead is toxic and exposure to lead dust particles can cause serious illness including brain damage especially in children. Pregnant women should avoid exposure. If adequate ventilation is not possible, wear a NIOSH approved respirator to avoid inhalation of the fumes and wear clothing designed to prevent skin contact. Clean up carefully with a HEPA vacuum and a wet mop. Before starting your project, you can find out how to protect yourself and your family by contacting the National Lead Information Hotline at 1-800-424-LEAD or visit their website at www.epa.gov/lead.

General Surface Preparation: The performance of this product is dependent on the integrity and soundness of the substrate. All surfaces should be clean and free of any dirt, rust, grease, mill oils, mill scale, efflorescence, organic growth, mildew or other contaminants that might adversely affect the adhesion and performance of this product. Any failed or deteriorated caulk or patching compound should be removed and replaced. Unpainted surfaces should be primed in accordance with manufacturer's recommendations. Glossy substrates should be deglossed prior to painting. **Plaster:** Plaster, hardcoat, skim coat or other alkaline surfaces should be allowed to cure for at least 30 days prior to priming with an alkali resistant primer.

New Concrete, Stucco and Masonry Surfaces: New concrete and masonry should cure for at least 30 days and preferably 90 days prior to painting. The PH of the substrate must be between 7 - 9 prior to application of this primer. Block mortar joint should cure for at least 30 days prior to priming. Fill block with appropriate blockfiller. **New Wood:** Unpainted wood or wood in poor condition should be sanded smooth, wiped clean and then primed. Any knots or resinous areas must be primed before painting. Countersink all nails, putty flush with surface, then prime with a quality stain blocking primer. **Ferrous Metal:** The surface must be cleaned thoroughly to remove any dust, rust, and surface contaminants and then primed with a corrosion resistant primer.

Directions for Use

Application: Mix thoroughly prior to use and occasionally during the application process. Product should be applied by brush, roller or airless spray. Apply coating evenly by maintaining a "wet edge" and working the material deep into the cracks and voids in the substrate. When using roller application, product should be applied in a downward direction to allow for a uniform finish. When using airless spray application "back rolling" is recommended to work the material into the pores, cracks and voids. **Brush:** Use quality nylon, polyester or combination nylon/polyester. **Roller:** Use a 3/8" to 3/4" synthetic, lamb's wool or mohair roller cover, depending on texture or surface porosity. **Airless:** Use a tip size between .011 and .015. Tip size should reflect the type of equipment and pressure being used, with a maximum pressure of 1000 PSI.

Thinning: Do not thin. Clean Up: Tools should be cleaned immediately after use with warm soapy water. Spray equipment should be flushed thoroughly after each use. **Dry Time and Curing:** Apply at spread rate of 275-390 square feet per gallon depending on the texture and porosity of the surface. Allow the to dry for 1 to 2 hours before recoating, or for best results overnight. Do not use when air, surface or product temperatures are below 50°F or above 100°F.

Safety

CAUTIONS: KEEP OUT OF REACH OF CHILDREN! DO NOT TAKE INTERNALLY! USE ONLY WITH ADEQUATE VENTILATION! Avoid prolonged contact with skin, and breathing of dust, vapors or spray mists. Avoid contact with eyes. Ensure fresh air entry during application and drying. Wear an appropriate fitted respirator (NIOSH approved.) Wear eye protection. Wash skin thoroughly after handling. Close container after each use and store in a secure, shaded and dry location. **First Aid:** In case of eye contact immediately flush with plenty of water for 15 minutes and get medical attention immediately. If swallowed do not induce vomiting and get medical attention immediately.

Storage and Disposal

Product should be kept from freezing temperatures or temperatures above 95°F. Refer to your local city or county government for instructions on disposal options.

Florida Paints believes the technical data represented in this technical bulletin to be current and up to date. However, Florida Paints makes no warranties or guarantees either expressed or implied. Florida Paints claims no responsibility from damages incurred from use by either the purchaser or user of the product.

PDS 3690-92 1807



Please excuse the small print used on this document but most paint company datasheets are two pages long. By squeezing all this information on one page we are doing our part to save a few trees.