

Aquatra



FLORIDA PAINTS

Industrial DTM Acrylic Enamel
Interior / Exterior

Satin Finish • **5320**
Semi-Gloss Finish • **5330**
Gloss Finish • **5340**

Product Description

Aquatra Industrial DTM Acrylic Enamel is specially formulated hybrid 100% acrylic polymer industrial enamel. It provides superior high performance qualities, similar to alkyd-based industrial enamel coatings. It offers superior flow and leveling characteristics, provides excellent coverage, and dries to a hard, tile-like finish that provides excellent durability. It resists moisture, salt spray, alkali, mildew, mild chemical washings, staining, fading and corrosion. Its special formulation also allows for use as direct-to-metal industrial acrylic enamel

Recommended Substrates

- Ferrous & non-ferrous metals
- Wood doors and trim
- Drywall and plaster
- Masonry and concrete

Product Features

- 100% acrylic formula
- Excellent durability and coverage
- Tile-like finish
- Excellent color and gloss retention
- Moisture and mildew resistant
- Low odor and non-yellowing
- Soap and water clean up

Product Limitations

This product is for use on properly prepared above grade vertical substrates. Do not apply to horizontal surfaces or areas that come in constant contact with moisture or standing water.

Available bases | 5320: WB | TB | DB | AB
Available bases | 5330: WB | TB | DB | AB
Available bases | 5340: WB | TB | DB | AB

Application: Brush, roller, airless or conventional spray
Dry time @ 50% RH*: 1 HR to touch
4 - 6 HRS recoat

*dry times listed may vary according to the relative humidity, temperature, film build, color and air movement of the application environment

Flash Point: Nonflammable >200°F
Clean Up: Soap and water

Compliance

These products are VOC compliant based on limits provided by EPA.

Product Data

Product Type: **Waterborne / 100 % Acrylic**

	5320	5330	5340
Gloss @60°:	15-25	44-55	65+

Wt Solids ±2%:	52%	49%	47%
Vol Solids ±2%:	35%	34%	35%

Wet Film Mils:	4.0 - 5.3	4.0 - 5.3	4.0 - 5.3
Dry Film Mils:	1.4 - 1.8	1.4 - 1.8	1.4 - 1.8
Coverage / Gal*	300 - 400	300 - 400	300 - 400

* coverage and wet and dry millage will vary by substrate type and porosity.

VOC gms p/L**:	<250	<250	<100
----------------	------	------	------

** less exempt solvents and before the addition of colorant

Viscosity KU ±5:	107	103	100
------------------	-----	-----	-----

Surface Preparation

Caution! There is the potential to release lead dust if you sand scrape or remove old paint. Lead is toxic and exposure to lead dust particles can cause serious illness including brain damage especially in children. Pregnant women should avoid exposure. If adequate ventilation is not possible, wear a NIOSH approved respirator to avoid inhalation of the fumes and wear clothing designed to prevent skin contact. Clean up carefully with a HEPA vacuum and a wet mop. Before starting your project, you can find out how to protect yourself and your family by contacting the National Lead Information Hotline at 1-800-424-LEAD or visit their website at www.epa.gov/lead.

General Surface Preparation: The performance of this product is dependent on the integrity and soundness of the substrate. All surfaces should be clean and free of any dirt, rust, grease, mill oils, mill scale, efflorescence, organic growth, mildew or other contaminants that might adversely affect the adhesion and performance of this product. Any failed or deteriorated caulk or patching compound should be removed and replaced. Unpainted surfaces should be primed in accordance with manufacturer's recommendations. Glossy substrates should be deglossed prior to painting. **Drywall:** Nails or screws should be countersunk, and they along with any indentations should be mudded flush with the surface, sanded smooth and cleaned to remove any dust, then primed or sealed prior to painting the substrate. **Plaster:** Plaster, hardcoat, skim coat or other alkaline surfaces should be allowed to cure for at least 30 days prior to priming with an alkali resistant primer. **New Concrete, Stucco and Masonry Surfaces:** New concrete and masonry should cure for at least 30 days and preferably 90 days prior to painting. The PH of the substrate must be less than 10 prior to priming with an alkali resistant primer. Block mortar joint should cure for at least 30 days prior to priming. Fill block with appropriate blockfiller. **New Wood:** Unpainted wood or wood in poor condition should be sanded smooth, wiped clean and then primed. Any knots or resinous areas must be primed before painting. Countersink all nails, putty flush with surface, then prime with a quality stain blocking primer. **Ferrous Metal:** The surface must be cleaned thoroughly to remove any dust, rust, and surface contaminants and then primed with a corrosion resistant primer.

Directions for Use

Application: Mix thoroughly prior to use and occasionally during the application process. Product should be applied by brush, roller or airless spray. Apply coating evenly by maintaining a "wet edge" and working the material deep into the cracks and voids in the substrate. When using roller application, product should be applied in a downward direction to allow for a uniform finish. When using airless spray application "back rolling" is recommended to work the material into the pores and reduce pinholes in the film. **Thinning:** Thinning is not required under normal conditions. **Clean Up:** Tools should be cleaned immediately after use with warm, soapy water. Spray equipment should be flushed thoroughly after each use. **Brush:** Use quality nylon or polyester bristle brushes. **Roller:** Use a 3/8" to 3/4" synthetic or lamb's wool cover depending on porosity. **Airless:** Minimum tip size between .015 - .019. Tip size should reflect the type of equipment and pressure being used. **Dry Time and Curing:** Do not use when air surface or product temperatures are below 50°F or above 100°F. Cleaning should not occur until 30 days after the initial application.

Safety

CAUTIONS: KEEP OUT OF REACH OF CHILDREN! DO NOT TAKE INTERNALLY! USE ONLY WITH ADEQUATE VENTILATION! Avoid prolonged contact with skin, and breathing of dust, vapors or spray mists. Avoid contact with eyes. Ensure fresh air entry during application and drying. Wear an appropriate fitted respirator (NIOSH approved.) Wear eye protection. Wash skin thoroughly after handling. Close container after each use and store in a secure, shaded and dry location. **First Aid:** In case of eye contact immediately flush with plenty of water for 15 minutes and get medical attention immediately. If swallowed do not induce vomiting and get medical attention immediately.

Storage and Disposal

Product should be kept from freezing temperatures or temperatures above 95°F. Refer to your local city or county government for instructions on disposal options.

Florida Paints believes the technical data represented in this technical bulletin to be current and up to date. However, Florida Paints makes no warranties or guarantees either expressed or implied. Florida Paints claims no responsibility from damages incurred from use by either the purchaser or user of the product.

PDS 5320-30-40 1808



Please excuse the small print used on this document but most paint company data sheets are two pages long. By squeezing all this information on one page we are doing our part to save a few trees.

Florida Paints and Coatings, LLC

78 3rd Street | Winter Garden, Florida 34787
407.986.1000 | info@FloridaPaints.com | FloridaPaints.com